

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: B29C 67/00, B29B 13/02, B29C 41/34	A1	(11) International Publication Number: WO 98/51477 (43) International Publication Date: 19 November 1998 (19.11.98)
(21) International Application Number: PCT/NL98/00261 (22) International Filing Date: 12 May 1998 (12.05.98) (30) Priority Data: 1006059 14 May 1997 (14.05.97) NL (71)(72) Applicant and Inventor: <u>VAN DER GEEST</u> , Adrianus, Franciscus [NL/NL]; Prins Bernhardstraat 39A, NL-2202 LG Noordwijk (NL). (74) Agent: BAKKUM, R., J.; Van Exter Polak & Charlouis B.V., P.O. Box 3241, NL-2280 GE Rijswijk (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>In English translation (filed in Dutch).</i>
(54) Title: METHOD AND DEVICE FOR PRODUCING A SHAPED BODY		
(57) Abstract Method for producing a shaped body, which method comprises the following steps: (1) applying a layer of pulverulent material to a surface, (2) patternwise applying at least one liquid to the layer of pulverulent material, forming a layer of patternwise bound-together pulverulent material, (3) repeating steps (1) and (2) a predefined number of times, so that a number of successive layers of patternwise bound-together powder, is formed, the successive layers of bound-together pulverulent material together forming the shaped body, and (4) removing the unbound powder, in which the liquid comprises water and the pulverulent material comprises at least one component which forms a binder after contact with water in step (2).		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

Method and device for producing a shaped body

The present invention relates to a method for producing a shaped body, which method comprises the following steps:

- (1) applying a layer of pulverulent material to a surface,
- 5 (2) patternwise applying at least one liquid to the layer of pulverulent material, forming a layer of patternwise bound-together pulverulent material,
- (3) repeating steps (1) and (2) a predefined number of times, so that a number of successive layers of
- 10 patternwise bound-together powder, is formed, the successive layers of bound-together pulverulent material together forming the shaped body, and
- (4) removing the unbound powder.

A method of this kind is known from EP-A-0,431,924.

15 According to this European patent application, a binder is applied as the liquid to the layer of powder applied on the surface, so that a layer of patternwise bound-together powder is produced. Generally, this takes place using one or more inkjet cartridges. However, a drawback of this

20 method is that the risk of the inkjet cartridges becoming blocked by the binder is high, certainly if a conventional inkjet printer is used. Furthermore, the use of a liquid binder has the disadvantage that it is generally slightly sticky and is therefore more difficult to handle.

25 The object of the present invention is to provide a solution to these problems and to this end is characterized in that the liquid comprises water and the pulverulent material comprises at least one component which forms a binder after contact with water in step (2).

30 The advantage of this method is that a liquid is used which is not in itself sticky, so that this liquid is easy to handle and that the risk of blockage when inkjet cartridges are used is minimal.

Of course the use of water is very environmentally

35 friendly. In the method according to the invention all the respective components are easy to handle.

This latter factor is a major advantage in

particular when using the so-called "drop-on-demand" inkjet cartridges. A drop-on-demand inkjet cartridge of this nature is known and generally comprises two rows of openings which deliver drops of the liquid to be sprayed
5 out when an electrical signal is received.

It is known per se from EP-A-0,431,924 to use a solvent as a liquid for binding the pulverulent material. The use of water containing liquids, which with a component from the pulverulent material in step (2) form a binder is
10 however not disclosed.

It is also known from EP-A-0,431,924 to heat the bound-together layers of powder, optionally during the application of the liquid binder, in order to promote hardening of the bound-together powder and to stimulate any
15 chemical curing reactions which take place at elevated temperature.

In the method according to the invention, it is preferred to dry the bound-together layers of powder, by heating them, after each execution of step (1) and/or (2)
20 or after every two or more executions of step (1) and/or (2). Particularly preferably, drying is carried out after every two to six executions of step (1) or (2). This heating can take place in numerous ways, for example by means of hot air, infrared irradiation and exposure to
25 microwaves. However, in the context of the present invention it has been found that very good results are obtained if the drying is carried out immediately after step (1) and before step (2) by placing a heated plate on or just above the layer of pulverulent material which was
30 applied last. The advantage of carrying out drying after step (1) is that the layer of powder which was applied last is still dry, with the result that there will be less tendency for powder to adhere to the plate when the plate is placed on the layer of powder which was applied last.
35 The temperature to which heating is carried out is dependent on the type of powder which is employed. However, the temperature preferably lies below the melting temperature of that component of the powder composition which has the lowest melting point. The temperature will

generally lie between 50 and 120°C. If desired, the heated plate can also be used to apply pressure to the applied layer of powder.

The water containing liquid which is applied to
5 each layer of pulverulent material is preferably applied in the form of one or more fine jets of droplets. Particularly preferably, the liquid is applied in the form of a plurality of fine jets of droplets, the liquids in the different jets being of different colours. This can be
10 achieved very effectively by making use of an inkjet printer, which are known per se.

It is also possible to produce coloured objects by making use of different colours. The locations where each specific colour is to be applied to the shaped body to be
15 produced can be set accurately by means of correctly programming a connected computer. Techniques of this kind are known per se for inkjet printers.

In addition to water the liquid used preferably also comprises 1-50% by weight, preferably 5-25% by weight,
20 of one or more flow promoters. Flow promoters of this nature are surface-active agents and are intended to reduce the surface tension, so that the liquid can be sprayed out of the very small openings in the inkjet cartridges in drops. Examples of suitable flow promoters are glycols,
25 such as diethylene glycol and monoethylene glycol, and lower alkanols, such as ethanol, 1-propanol and 2-propanol. It is also possible to use combinations of two or more flow promoters of this nature. A very suitable combination is, for example, a mixture of diethylene glycol and 2-propanol.

30 The liquid may contain one or more colorants. If a plurality of inkjet cartridges are used, it is possible to use a plurality of liquids, the colours of which differ from one another, so that a shaped body comprising different colours can be produced.

35 As has been mentioned, the pulverulent material comprises a component which, as a result of coming into contact with the liquid sprayed on, forms a binder (the "adhesive component"). In addition, the powder may comprise a filler. If fillers are applied the shaped body obtained

by the method according to the invention can for instance be sintered, fired or annealed, to remove the binder component and to obtain a shaped body from the material of the filler. Examples of fillers are metal powder, glass beads, glass fibres, ceramic materials, plastics, silica, sand etc. Thus it is for example possible to produce a shaped body completely consisting of glass, steel, iron etc.

Preferably the pulverulent material comprises apart from the component, which as a result of coming into contact with the water sprayed, forms a binder, a secondary binder. Such a secondary binder comprises in particular a thermosetting material or thermoplastic material. Thermosetting materials are materials which cure under the influence of heat, such as polyester powder coatings. An example of this is the polyester powder coating type LT produced by Lakfabriek Korthals B.V. Thermoplastic materials are materials which soften or melt by heating and which solidify again upon cooling.

The above thermosetting and thermoplastic materials are called secondary binders in the present context. The presence of secondary binders provides the possibility to manufacture quickly and simple a shaped body by means of the method according to the invention, which can be additionally reinforced after completion by a heat treatment.

Suitable adhesive components are in particular powders which form a binder after coming into contact with the water containing liquid. Examples are dextrin powder, (carboxy)methylcellulose, wallpaper adhesive powder, gelatin, inulin, gum arabic, polyvinyl alcohol, cement, plaster, a water soluble salt and finely ground granulated sugar. A powder in which the adhesive component is polyvinyl alcohol, (carboxy)methylcellulose, gelatin and/or dextrin is preferred. Examples of suitable polyvinyl alcohol powders are completely or partially hydrolysed polyvinyl alcohols, such as those which are sold under the trade name Mowiol. Suitable grades are, for example, Mowiol 3-83, Mowiol 18-88 and Mowiol 10-98. A polyvinyl alcohol

powder can be prepared by grinding a polyvinyl alcohol granulate at a temperature below the glass transition temperature of polyvinyl alcohol, for example under liquid nitrogen. An example of a commercially available dextrin is
5 37-LAC-19, sold by the Avebee company.

The particle size of the powder particles generally varies from 25 to 250 μm , and preferably lies between 50 and 175 μm . If the powder particles are larger than 250 μm , the dimensional accuracy of the shaped body to be formed is
10 excessively determined by the particle size of the powder, which is generally undesirable. An example of a powder composition which can be used is a composition which contains approximately 3 parts by volume of glass beads (approx. 50-100 μm), 3 parts by volume of polyester powder
15 coating and 1 part by volume of dextrin. The powder composition may also comprise polyvinyl alcohol, optionally with the addition of a secondary binder and/or a filler.

After all the layers of bound-together pulverulent material have been formed, the surplus powder which has not
20 been bound together is removed. The shaped body obtained is then preferably placed in an oven in order to remove the liquid still present and to allow any powder components present, like a secondary binder to perform the respective function. The strength of the shaped body is optimized in
25 this way. If desired, before or after heating in an oven, if this takes place, the shaped body may be covered on the outside with a (colourless) lacquer or varnish. As well as having an advantageous effect on the strength of the shaped body, this may also be beneficial to the colourfastness of
30 the shaped body, particularly if it is produced in different colours.

It is preferred however to subject the combination of non-binded powder and the manufactured shaped body after step (3) to a drying treatment. Thus, a stronger product is
35 obtained. Hereby no danger exists for possible deformation of the shaped body during the subsequent step (4) wherein the non-bound powder is removed from the shaped body. Such a drying treatment can for example be effected in an oven.

The shaped bodies which can be produced in the

method according to the invention are employed in a variety of fields. By way of example, the shaped bodies can be used to make scale models of, for example, furniture, means of transportation (cars, trains, aircrafts and the like),
5 molecules, toys, prostheses and other implements and decorative objects. The method is also very suitable for producing models of buildings and landscapes, as well as moulds for producing, for example, plaster objects.

If the powder composition contains, in addition to
10 the adhesive component, a filler, it may be advantageous to bind the adhesive component to the filler in advance. To this end, filler and adhesive component and any other components can be mixed in advance, in the presence of water or some other suitable liquid, after which the
15 composition is dried and, if necessary, comminuted.

As an inkjet printer inkjet printers can be used which are known and commercially available. An example of an extremely suitable inkjet printer is the HP-deskjet 850 printer of Hewlett Packard. The ink spraying part of this
20 printer is mounted such that this can print on top of the layer of powder. The printer comprises spraying openings for black ink and for three different base colours. By replacing the black ink by water with suitable flow promoters, it is provided for that with this device
25 articles can be manufactured of all possible combinations of colours.

Extremely suitable inkjet cartridges are the commercially available drop-on-demand inkjet cartridges of the type HP 51645 (also of Hewlett Packard). Such an inkjet
30 cartridge comprises about 300 spray openings.

In the following the invention will be illustrated by means of an example.

EXAMPLE

A 3D model of a Porsche was downloaded from Internet
35 (www.3dcafe.com). With the programm 3D-Studio this model was coloured and exported to a Polyray file. From this Polyray file with a special programm 112-sections were calculated. All locations on the sections having a smaller distance than 1 mm from the closest outer side of the model

obtained the colour of said closest outside. These sections were sent to a printer according to EP-A-0,431,924, the printing part being derived from a HP-deskjet. Thus, within 20 min a model of the car was printed, which car contained
5 a completely coloured outside.

As a pulverulent material finely ground polyvinyl alcohol was used with a particle size of about 120 μm . Printing was performed with water and water based ink (HP deskjet ink) wherein the black ink was substituted by
10 water.

Claims

1. Method for producing a shaped body, which method comprises the following steps:
 - (1) applying a layer of pulverulent material to a surface,
 - (2) patternwise applying at least one liquid to the layer of pulverulent material, forming a layer of patternwise bound-together pulverulent material,
 - 5 (3) repeating steps (1) and (2) a predefined number of times, so that a number of successive layers of patternwise bound-together powder, is formed, the successive layers of bound-together pulverulent material together forming the shaped body, and
 - 10 (4) removing the unbound powder, **characterized in that**, the liquid comprises water and the pulverulent material comprises at least one component which forms a binder after contact with water in step (2).
2. Method according to claim 1, **characterized in that**,
15 drying is carried out after each execution of step (1) and/or (2) or after every two or more executions of step (1) and/or (2).
3. Method according to claim 2, **characterized in that**,
20 drying is carried out after every two to six executions of step (1) and/or (2).
4. Method according to claim 2 or 3, **characterized in that**, drying is carried out by placing a heated plate on or just above the layer of pulverulent material which was applied last immediately after step (1) and before step
25 (2).
5. Method according to one or more of the preceding claims, **characterized in that**, the liquid is applied in the form of one or more fine jets of droplets.
6. Method according to claim 5, **characterized in that**,
30 the liquid is applied in the form of a plurality of fine jets of droplets, the liquids in different jets being of different colours.
7. Method according to one or more of the preceding claims, **characterized in that**, component of the pulverulent
35 material which forms a binder with water is polyvinyl

alcohol, (carboxy)methylcellulose, gelatine and/or dextrin.

8. Method according to one or more of the preceding claims, **characterized in that**, the pulverulent material in addition to the component which forms the binder comprises
5 a filler.

9. Method according to one or more of the preceding claims, **characterized in that**, the pulverulent material in addition to the component which forms a binder comprises a secondary binder.

10 10. Method according to claim 9, **characterized in that**, the secondary binder comprises a thermosetting material or a thermoplastic material.

11. Method according to one or more of the preceding claims, **characterized in that**, the combination of non-bound
15 powder and the manufacture shaped body are subjected to a drying treatment after step (3).

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 98/00261

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B29C67/00 B29B13/02 B29C41/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29C B29B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 93 25336 A (MASSACHUSETTS INST TECHNOLOGY) 23 December 1993	1-6, 8-10
Y	see claims 27, 39	7
Y	EP 0 081 218 A (FREUDENBERG CARL FA) 15 June 1983 see the whole document	7
A	EP 0 431 924 A (MASSACHUSETTS INST TECHNOLOGY) 12 June 1991 cited in the application see the whole document	1-11
A	GB 2 233 928 A (BROTHER IND LTD) 23 January 1991 see the whole document	1-11

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

28 August 1998

Date of mailing of the international search report

03/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mathey, X

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 98/00261

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9325336 A	23-12-1993	US 5387380 A	07-02-1995
		CA 2136748 A	23-12-1993
		EP 0644809 A	29-03-1995
		JP 7507508 T	24-08-1995
EP 0081218 A	15-06-1983	JP 1018182 B	04-04-1989
		JP 1534835 C	12-12-1989
		JP 58098464 A	11-06-1983
		US 4570311 A	18-02-1986
EP 0431924 A	12-06-1991	US 5204055 A	20-04-1993
		CA 2031562 A, C	09-06-1991
		DE 69025147 D	14-03-1996
		DE 69025147 T	05-09-1996
		JP 2729110 B	18-03-1998
		JP 6218712 A	09-08-1994
		US 5340656 A	23-08-1994
		US 5387380 A	07-02-1995
GB 2233928 A	23-01-1991	JP 2307728 A	20-12-1990
		JP 2738016 B	08-04-1998
		JP 2307730 A	20-12-1990
		JP 2697136 B	14-01-1998
		JP 2697137 B	14-01-1998
		JP 3114731 A	15-05-1991
		JP 2307731 A	20-12-1990
		JP 2697138 B	14-01-1998
		JP 2307732 A	20-12-1990
		JP 2697139 B	14-01-1998
		JP 2307733 A	20-12-1990
		JP 2699548 B	19-01-1998
		JP 2310025 A	25-12-1990
		JP 2738018 B	08-04-1998
		JP 2738019 B	08-04-1998
		JP 3015519 A	23-01-1991
		JP 3039234 A	20-02-1991
		US 5059266 A	22-10-1991